

**RD-T-17-01-02** 

## **REOLOSIL**<sup>®</sup>

**FM-22** 

Hydrophilic Fumed Silica

Reolosil FM-22 is very fine amorphous silicon dioxide made by combustion of high purity silicon tetrachloride with oxygen and hydrogen.

Reolosil FM-22 is fluffy white powder and are used in many kind of coating systems because of its unique property that is fine particle size, high purity, high transparency, excellent dispersion.

It is used as matting agent in Paints and Coatings, like water-based dispersion coatings and topcoats.

## **Typical Properties**

Specific Surface Area (BET)	215-295 m²/g
Average Particle Size (Beckman Coulter MS3)	2.4-3.3µm
Bulk Density	50 g/L (approximately)
pH (4% suspension)	6.0-9.5
Moisture Content (Dry up, %) *1	< 8.0 %

The data represents typical values (no product specification).

<sup>\*1</sup> When leaving plant

## Characteristic Properties Outstanding matting effect and transparency

## **Typical Packaging Forms** Packaged in 10 kg / paper bag.

The recommendations and suggestions given in this literature are made without any representation or warranty as they are presented for your own investigation and verification. The Products discussed are sold without warranty, expressed or implied. Statements concerning specific applications of our products or the processes described should not be construed as permission or recommendation to use the same in a manner that infringes upon any patent, or to use a patented invention without license. Before use, refer to the Safety Data Sheet (SDS) for these products for important safety information.